



## Urea Formaldehyde Resin Powder

Appearance	-	white powder
Volatile matter	%	1.5 appr.
Free Formaldehyde	%	1.0 max.
Bulk density	kg/dm <sup>3</sup>	0.45
Storage life @ 25 °C	months	12 min.

### 50% Water dispersion (1 part resin + 1 part water)

PH @ 25 °C	-	8.1
Viscosity @ 30 °C	mP a.s	125
Stability @ 25 °C	days	5

**SAMINO 800**  
Urea-Formaldehyde Resin  
meeting ISO standards ISO 9001 & ISO 14001 requirements

### Our Offer

Min. quantity 1 20 feet FCL (15 MT on palette)  
Payment: 30% in advance and 70% against B/L copy  
Delivery time: 1 week

